



STOPS RUST® WITH TURBO SPRAY SYSTEM

DESCRIPTION AND USES

Rust-Oleum® Innovative Turbo Spray System delivers the same trusted protection of traditional Stops Rust and now gets the job done 4x faster. Super tall fan spray coats the surface in fewer passes for faster projects. Professional spray equipment results without messy cleanup. 24 ounce can optimized for large jobs. Fun and exciting for users to tackle large, intimidating jobs in minutes.

Rust-Oleum Stops Rust® Enamel Sprays are designed to provide a durable protective coating with excellent rust prevention, and excellent resistance to abrasion, fading, chipping, and dulling. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Rust-Oleum Stops Rust Enamel Sprays are ideal for ferrous, non-ferrous metal and wood surfaces. It features a comfort tip with a wider finger pad to reduce fatigue caused by continuous spraying and can be used with the Comfort Spray Grip for easier completion of larger projects. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
334128	Gloss Black
334133	Gloss White

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°-90°F (10°-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of a Stops Rust® Primer provides added corrosion protection, superior adhesion and hiding and is especially recommended for bare wood and metal.

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 18-24" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. It is recommended to apply a light first coat, target 50% coverage. Apply 2 or more light coats a few minutes apart.

DRY AND RECOAT TIMES

Based on 70°F (21°C) 50% relative humidity. Allow more time at cooler temperatures. Dries tack-free in 2-4 hours, to handle in 5-9 hours, and is fully dry in 24 hours. Apply a second coat within 1 hour or after 48 hours.

CLEAN UP

Wipe off tip before storing. Clean up wet paint with Xylene or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

After use, turn can upside down and press spray nozzle until spray is clear to prevent clogging. If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other objects into the stem.

	TECHNICAL DATA	SRT-44
	STOPS RUST® WITH TURBO SPRAY SYSTEM	

PHYSICAL PROPERTIES

STOPS RUST WITH TURBO SPRAY SYSTEM		
Resin Type		Oil modified Alkyd
Pigment Type		Varies depending on color
Solvents		Acetone, N-Butyl Acetate, Aromatic Hydrocarbons
MIR		0.95 max
Fill Weight		24 oz.
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assume 15% material loss)		24-40 sq.ft./can
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	Before 1 hour and after 48 hours
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.