

• TRUSTED QUALITY SINCE 1921 •
RUST-OLEUM®
 SPECIALTY

RUST-OLEUM® DRY ERASE KIT

DESCRIPTION AND USES

Rust-Oleum® Dry Erase Paint is a smooth, hard finish that creates a unique writable-erasable surface. Once dry, simply use any dry erase markers to draw or write messages and then erase. Application is easy and it has minimal odor making it safe to use indoors. Dry Erase is ideal for use on interior surfaces such as drywall, Masonite, wood, concrete and metal. Not recommended for use in commercial applications.

PRODUCT

SKU	DESCRIPTION (Kit)
241140	Dry Erase White

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt, and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Lightly sand surface that is to be painted. Remove dust from sanding with a lint-free cloth. If applying dry erase on a new piece of drywall, Masonite, concrete or wood, use a white latex primer first (follow manufacturer's directions). A primer is not needed for existing drywall that is already painted or on metal surfaces.

WARNING! If you scrape, sand, or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

MIXING

Briefly stir each can before mixing. Pour Part A into Part B and stir thoroughly until the paint is uniform in color (about 2 minutes). No waiting time is required after mixing.

IMPORTANT! Apply activated Dry Erase Paint within 1 hour of mixing.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air and surface temperatures are between 50-90°F (10-32°C), and the relative humidity is below 85% to ensure proper drying.

With painter's tape, tape around the area you wish to paint before beginning. Pour paint into a paint tray. Use a dense foam roller that is designed to give a smooth finish. For smaller surfaces, use a foam brush.

For best results, apply over a white or light colored surface. When applying over darker surfaces, priming is recommended with a white/light color. The surface dries to the touch in 3-4 hours. After 1 hour, remove painter's tape that was used to mask the area. Then allow the Dry Erase surface to cure for 3 days before applying any markings. Once fully cured, dry erase markers may be applied to the surface and then wiped off with an eraser or lint-free cloth. If a slight mark remains after erasing, simply use a dry erase cleaner to remove the mark. Do not use any general household cleaner, abrasive cleaner, pads, or cloths. Let surface dry before using dry erase markers again.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Recoat after 24 hours.

CLEANUP

Clean brush and other application tools immediately with soap and water.

	TECHNICAL DATA	SPC-04
• TRUSTED QUALITY SINCE 1921 • RUST-OLEUM® SPECIALTY	RUST-OLEUM® DRY ERASE KIT	

PHYSICAL PROPERTIES

		DRY ERASE (WHITE, ACTIVATED)
Resin Type		Polyamine Epoxy Blend
Pigment Type		Titanium Dioxide
Solvents		Water, Glycol Ethers
Weight	Per Gallon	10.3 lbs.
	Per Liter	1.23 kg
Solids	By Weight	58.2%
	By Volume	48.4%
Volatile Organic Compounds		<50 g/l (0.42 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50µ)
Wet Film to Achieve DFT (unthinned material)		2.1-4.2 mils (53.3-106.7µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		50 sq. ft./16-ounce kit
Mixing Ratio		3.4 Fl. Oz. of Part A to 12.6 Fl. Oz. of Part B
Pot Life		Up to 1 hour
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	3-4 hours
	Recoat	24 hours
	Full Cure	3 days
Shelf Life		2 years Unopened
Flash Point		>200°F (93°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 800-481-4785
www.rustoleum.com

Form: GDH-1031
Rev.: 091824