

PRODUCT DATA SHEET

GEMCOAT PRECATALYZED LACQUER 510-005x Series

DESCRIPTION

This product line represents an intermediate step between our high quality water clear lacquers and our extremely durable conversion varnish series. The blending of these two technologies creates a product that demonstrates ease of application similar to a lacquer, while providing some of the performance characteristics normally associated with a conversion varnish. For wood substrates only. For interior use only.

Product	Numbers / Sheen
510-0050	Gloss(90°)
510-0051	Semi-Gloss(60°)
510-0052	Satin(30°)
510-0062	(20°)
510-0053	Flat(10°)
5	

PRODUCT ADVANTAGES

- ➤ HAPs & AIM Compliant
- ➤ User Friendly
- ➤ No Catalyst Required
- ➤ Water Clear
- ➤ Self Sealing
- ➤ Meets KCMA and ASTM
 Performance Requirements
 When Applied to Manufacturer's
 Specifications
- > Pthalate Free
- ➤ Non Photo Chemically Reactive

Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.

COATING PROPERTIES

Viscosity: 27" #2 Zahn Weight Solids: 27-28% Volume Solids: 20%

Weight/Gallon: 7.68-7.73 lbs./gal

Coverage: 318-325 sq. ft. per gallon at one

mil dry film thickness.

VOC (reg./coating): 5.49-5.53 lbs./gl. or 658-

662 g/

VOC (act./material): 5.06-5.10 lbs./gl. or

607-611g/l

VOC Ratio: 2.37-2.48 lbs. VOC/lbs. solids HAPS Ratio: 0.65 -0.68 lbs. HAPS/lbs. solids

Dry Times:

Air Dry: at 78°F, relative humidity 50%

To touch: 8 minutes
To Handle: 12 minutes
To sand/recoat: 30-45 minutes

Force Dry:

Flash: 8-10 minutes Bake: 15 minutes @110°F Cool down: 10 minutes Stack: 1 hour after cool down

Relative humidity will affect the speed of drying. Ideal conditions are 75°F or warmer at 50% humidity or less. Dry time will be faster at higher temperatures and lower humidity and equally slower at colder temperatures and higher humidity.

Dry Film Thickness: Maximum DFT for a complete system must not exceed 3 dry mils.

Pot Life: N/A

Shelf Life: 12 months @77° F if unopened and stored in a cool dry area. Always rotate

stock.

Storage: Keep away from heat or sparks.

PREPARATION INSTRUCTIONS

Catalyzation: This product comes precatalyzed. Do NOT add catalyst.

Reduction:

Thinning: This product is supplied ready to spray. If needed due to conditions in your facility use SOL-0500, SOL-9011 HAPs Free Thinner or SOL-9059 HAPs Free reducer at levels not to exceed 10% by volume*

Retarder: If a slower dry time is desired, use SOL-9012 Haps Free Retarder at levels not to exceed 4% by volume*

Note: Effective dry times will be lengthened if retarder is added

*Thinning this material may result in increasing the VOC levels of this product. Refer to your local regulations before thinning.

Approved Companion Products 210-0215

Updated August 8th 2014

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPILED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER. CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDRENI BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

PRODUCT DATA SHEET 510-005X SERIES CONTINUED

Substrate preparation:

New wood: Remove any dirt, grease, glue or other contaminants. Moisture content of wood should be 7-9%.

Sand to 150-180 grit. Proper sanding of wood is absolutely critical to achieve the best color development and adhesion of the coating to the substrate.

Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish same as new wood.

Mixing Instructions:

Mix material thoroughly before and during use. Material may be mixed by hand or mechanical agitation at moderate speed.



Application:

If staining, apply the approved Gemini stain of your choosing and let dry per the instructions on the PDS for that particular stain. Using conventional, HVLP, airless, or air assisted equipment, apply this product at 3-4 wet mils per coat. Let dry a minimum of 30-45 minutes. Sand with 280-320 grit, no-fill sandpaper and remove sanding dust with clean compressed air, or tack rag. This product must be sanded in between coats to ensure proper adhesion.

This product may be used with a sealer or as a self-seal system. If a sealer is desired, we recommend a coating system comprised of one coat of 210-0215 applied at 3-4 mils wet film build and 1-2 coats of topcoat applied at 3-4 mils wet film build. If used as a self- seal system we recommend 2-3 coats of 510-005X series. Maximum dry film thickness of the complete system must not exceed 3 dry mils.



Recommended Tip Sizes:

Conventional Air 1.3-1.8mm HVLP 1.3-1.8mm

Airless 10-15 thousandths
Air Assisted Airless- 11-15 thousandths



Precautions:

These products are intended for Professional use only. Do not proceed if you are planning on mixing with other finishing systems or other manufacturer's products. Gemini will not be held liable for finish failures due to the improper use of our products or deviation from our finishing recommendations

Equipment:

All equipment used with this product must have plastic, stainless steel, or Teflon fluid passages and wetted parts

Containers:

We supply this material in a lined container. All containers used in conjunction with storage and/or application of this product must be stainless steel, plastic, or otherwise acid resistant.

Clean up:

Use SOL-9011 Non HAPs Thinner or SOL-9059 HAPs Free Reducer to clean up all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.

Care and cleaning of this finish: Use a mild dishwashing liquid and a damp cloth to remove food, grease, and other residue. Wipe dry. Do not use cleaners that contain ammonia, bleach, or abrasives as this may damage the finish.