

FAST DRY WOOD STAIN

Description

This high quality, interior alkyd-based wood stain applies easily and enhances the wood's natural grain with its intensified depth of color and clarity. Its rapid dry time and superior performance allow every project to be topcoated more quickly, granting a more efficient turnaround. Makes a great alternative to lacquer stains. Experience optimal results on all interior wood surfaces such as cabinets, doors, floors, furniture, and woodwork.

Surface Preparation

The wood surface must be clean, dry and free from dirt, wax, or grease. Sand the wood thoroughly, first with medium grit sandpaper, then progressing to a fine grit paper. Always sand in the direction of the wood grain. Sand smooth, then remove dust particles with a lint-free rag or a tack rag. If staining previously finished surfaces, first restore the surface to bare wood by completely removing the old finish, then follow the surface preparation directions listed above.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir well before and during use. Stain may be brushed, sprayed or wiped onto the surface. Before the stain dries, wipe off excess stain with a soft cloth. Allow stain to dry thoroughly before applying topcoat.

Mixing and Tinting

Achieve custom colors by intermixing Fast Dry Wood Stain colors or by adding up to 10 ounces of universal or industrial colorant per gallon to any Fast Dry Wood Stain or by adding colorant to Natural/Tint Base Fast Dry Wood Stain. Natural/Tint Base Fast Dry Wood Stain may be used to lighten a Fast Dry Stain color in any proportion or as a tint base to which colorant may be added for ultimate color selection. The amount of colorant added may affect performance and extend dry time.

Coverage

Approximately 500 square feet per gallon depending on the porosity and texture of the wood.

Dry Time

Oil-based finishes may be applied 30 minutes after wiping. Dry times may be extended due to humidity, low temperature, lack of air movement, excess stain application or lack of penetration. Be sure surface is thoroughly dry before topcoating. Ideal drying conditions recommended are 70° to 75°F and 35% to 50% humidity.

Product Codes

Available Sizes: Half-pint (16), Quart (04), and Gallon (01)

601	Natural
602	Golden Oak
603	Cherry
604	Red Mahogany
605	Provincial
606	Maple
607	Early American
608	Dark Mahogany
609	Cedar
610	Dark Walnut
611	Special Walnut
612	Spanish Oak
613	Fruitwood
614	Pickling White
616	Natural Walnut
617	Pecan
618	American Walnut
621	Rich Mahogany
623	Espresso
624	Aged Oak
625	Weathered Wood
626	Carbon Black

FAST DRY WOOD STAIN

Clean Up

Using a cleaning solvent, such as paint thinner or mineral spirits, is recommended for clean up. The use of paint thinners or mineral spirits may violate VOC compliancy in your area. Check with your local government agencies to ensure proper compliancy.

DANGER: Rags, steel wool, sanding residue, and other wastes used or soaked with this product may spontaneously catch fire if improperly discarded. No ignition source is required for these wastes to start on fire by themselves. Immediately place rags, steel wool, sanding residue, and other wastes used or soaked with this product in a sealed, water-filled metal container. Dispose of in accordance with local fire regulations.

Recommended Finish Coat

We recommend Old Masters clear finishes. However, Fast Dry Wood Stain can be topcoated with virtually any finish including professional finishes such as lacquers and conversion varnishes. Wait 24 hours before topcoating with a water-based clear finish.

Limited Warranty

Since Old Masters does not control the application of its products, nor is the condition of the surface to which they are applied, a Limited Warranty is provided. If the products do not perform as specified, for whatever reason, Old Masters liability will under no circumstances exceed the replacement of the product.

Technical Data

Product Information

Solids by Volume	29% to 32%
Weight per Gallon	7.15 to 8.30 lbs
Vehicle	Alkyd
Viscosity at 77°F	12 to 17 secs. Zahn Cup #2
Flash Point	102°F Tag Closed Cup
Recommended Thinner	Do not thin. Used as packaged.
VOCs	550 g/L

Coverage

Practical Coverage Depending on the Porosity and Texture of the Wood	500 sq ft/gal
Coverage @ Recommended DFT	N/A
Recommended DFT Per Coat	N/A

Dry Time

At 70°F and 50% Relative Humidity	30 to 60 minutes
-----------------------------------	------------------